



# SPECIFICATION SHEET

## MTX-XS

CHEMISTRY	Carbon: 0.10 to 0.15% Silicon: 0.10 to 0.25% Manganese: 1.20 to 1.50% Aluminum: 0.05 to 0.15% Phosphorus: 0.035% max. Sulfur : 0.035% max.	SAE J2175																		
SCREENING	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;"><u>Sieve</u></th> <th style="text-align: left;"><u>Opening</u></th> <th style="text-align: left;"><u>Specification</u></th> </tr> </thead> <tbody> <tr> <td>10</td> <td>0.0787</td> <td>A/P</td> </tr> <tr> <td>12</td> <td>0.0661</td> <td>5% max.</td> </tr> <tr> <td>14</td> <td>0.0555</td> <td></td> </tr> <tr> <td>16</td> <td>0.0469</td> <td>85% min.</td> </tr> <tr> <td>18</td> <td>0.0331</td> <td>96% min.</td> </tr> </tbody> </table>	<u>Sieve</u>	<u>Opening</u>	<u>Specification</u>	10	0.0787	A/P	12	0.0661	5% max.	14	0.0555		16	0.0469	85% min.	18	0.0331	96% min.	METALTEC
<u>Sieve</u>	<u>Opening</u>	<u>Specification</u>																		
10	0.0787	A/P																		
12	0.0661	5% max.																		
14	0.0555																			
16	0.0469	85% min.																		
18	0.0331	96% min.																		
HARDNESS	40 - 50 Rc, typical 44.5%	SAE J2175																		
% ROUNDS	> 65% non-spherical (length > 2 x width), typical 85%	METALTEC																		
% VOIDS AND HOLLOWES	< 10% voids and hollows, typical < 2%	SAE J2175																		
NON-MAGNETIC MATERIAL	< 1% non-magnetic material, typical <0.5%	SAE J2175																		
DENSITY	> 7 g/cc (wet method)	SAE J2175																		
DURABILITY	> 3000 passes (Ervin Test), typical 3500	METALTEC																		
PACKAGING	50 lb. bags, 2000 lb. drums, 2000 - 4000 lb. hoppers, bulk dump truck, other custom packaging available upon request.																			

*All abrasives supplied by Metaltec Steel Abrasive are proudly produced, processed and packaged by the teams at Metaltec's Canton, Michigan plant. Quality system registered to ISO 9001:2000 standard.*

**Metaltec Steel Abrasive Company**  
 41155 Joy Road  
 Canton, MI 48187  
 (734) 459-7900 phone  
 (734) 459-7907 fax